



EN 14592/A1



www.montana.lu

Certificate

Circular ring shank Joist Hanger Coil nails for structural timber products

Diameter = 3.3 mm Length = 38mm

Properties of the material used:

- non alloy wire rod in accordance with EN 10016-1 to 4
- tensile strength in accordance with EN 10218-1, minimum 700 N/mm²

Characteristic mechanical properties:

- | | |
|--|-------------------------------------|
| - Yield moment: | $M_{y,k} = 7732 \text{ Nmm}$ |
| - Withdrawal strength parallel to grain:
Timber: minimum characteristic density of 310 kg/m ³ | $f_{ax,0,k} = 1.65 \text{ N/mm}^2$ |
| - Withdrawal strength perpendicular to grain:
Timber: minimum characteristic density of 310 kg/m ³ | $f_{ax,90,k} = 4.66 \text{ N/mm}^2$ |
| - Head pull-through parameter:
(in steel plate - 0.9mm thick) | $f_{head,k} = 58.81 \text{ N/mm}^2$ |
| - Tensile capacity: | $f_{tens,k} = 5.04 \text{ kN}$ |

Durability (Corrosion Protection):

Bright - Service Class 1 or
Galv < 12 µm Service Class 1 or
Galv 12 µm Service Class 2 acc. to EN1995-1-1

